

MEGOLON S530

Flexible Sheathing Grade Compound

DESCRIPTION

MEGOLON S530 is a thermoplastic, halogen free, fire retardant, cable-sheathing compound.

APPLICATIONS

- This material has been specifically developed for telecommunication cable applications

PRODUCT BENEFITS

- Very good flexibility
- Low Young's Modulus
- Enhanced fire test performance with a high oxygen index

TECHNICAL PROPERTIES

Primary Properties	Unit	Nominal Value	Test Method
Tensile strength	MPa	11.5	IEC 60811-1-1
Elongation at break	%	180	IEC 60811-1-1
Oxygen Index	%	40	ISO 4589-2
Density	g/cc	1.58	ASTM D-792
Mooney viscosity (1+4 mins, 140°C)		50	ASTM D-1646
Melt Flow Rate (21.6 kg, 150°C)	g/10 mins.	1.5	ISO 1133

Mechanical Properties	Unit	Nominal Value	Test Method
Tear strength	N/mm	5	BS 6469:99.1
Tensile strength after 7 days at 100°C	MPa	14.5	IEC 60811-1-2
Variation	%	+26	
Elongation at break after 7 days at 100°C	%	130	IEC 60811-1-2
Variation	%	-28	

Thermo-mechanical Properties	Unit	Nominal Value	Test Method
Hot pressure at 80°C	%	33	IEC 60811-3-1
Hot deformation at 90°C	%	5	BS 6469:99.1
Cold elongation at -25°C	%	40	IEC 60811-1-4
Cold impact at -25°C	%	PASS	IEC 60811-1-4

Fire and Smoke Test Properties	Unit	Nominal Value	Test Method
Flammability temperature index	°C	300	ISO 4589-3
Halogen acid gas evolution	%	ZERO	IEC 60754-1
Corrosiveness of gases			IEC 60754-2
pH		4.5	
Conductivity	µS/cm	42	
Smoke density – Flaming mode	Ds max	48	ASTM E-662
Time to maximum	minutes	11	
Smoke density – Non-flaming mode	Ds max	350	ASTM E-662
Time to maximum	minutes	12	
Toxicity index		1.6	NES 713

Oil Resistance Properties			Tensile Strength (MPa)	Variation (%)	Elongation at Break (%)	Variation (%)	Volume Swell (%)
Medium	Temperature	Duration					
ASTM 2	23°C	7 days	11.5	0	140	-22	0
ASTM 2	70°C	4 hours	11	-5	171	-5	+1
SAE 20	70°C	4 hours	8.6	-25	207	+15	n/a
Diesel	23°C	7 days	5.2	-55	171	-5	+16

Electrical Properties	Unit	Nominal Value	Test Method
Dielectric constant at 50Hz		3.8	ASTM D-150
Dissipation factor at 50Hz		0.014	ASTM D-150
Insulation resistance at 20°C			BS 6469:99.2
Initial value	ohm.cm	6×10^{13}	
After 12 hours immersion in water	ohm.cm	1×10^{13}	

Other Properties	Unit	Nominal Value	Test Method
Hardness	Shore D	45	ASTM D-2240
Ozone resistance		PASS	ASTM D-470

Oct. 2006: This data was established by AlphaGary Manchester UK
Issue 5 – Jan. 7, 2004 (new logo – do'c)

AlphaGary Ltd., Beler Way, Melton Mowbray, Leicestershire LE13 0DG UK
AlphaGary Corporation, 170 Pioneer Drive, Leominster MA 01453 USA
info@alphagary.com or www.alphagary.com

Although AlphaGary believes these data are accurate as of the date hereof, they are provided for informational purposes only. It cannot be assumed that these data cover all uses, applications or conditions in connection with this material. Accordingly, AlphaGary makes no warranty, expressed or implied, that the product conforms to these data. Each customer or user of AlphaGary's materials is solely responsible for determining the suitability of the material(s) selected for the intended application. Each customer or user must conduct its own studies and gain all necessary approvals and certifications as required for the intended finished product.